

PA 1098285

101721 2003/012317
EPO - Munich
83
05. März 2004

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

November 26, 2003

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM
THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK
OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT
APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A
FILING DATE UNDER 35 USC 111.

APPLICATION NUMBER: 60/475,785

FILING DATE: June 05, 2003



By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS

E. Bornett

E. BORNETT
Certifying Officer

BEST AVAILABLE COPY

LAW OFFICES OF

JACOBSON HOLMAN
PROFESSIONAL LIMITED LIABILITY COMPANY

400 SEVENTH STREET, N. W.

WASHINGTON, D. C. 20004

(202) 638-6666

JACOBSON HOLMAN STERN

OF COUNSEL
MARVIN R. STERN
NATHANIEL A. HUMPHRIESTELEFAX:
(202) 393-5360
(202) 393-5351
(202) 393-5353E-MAIL: JPBJHIP@JH
INTERNET: WWW.JHIP.COM

*BAR OTHER THAN

June 5, 2003

Atty. Docket No.: P6891US0
CUSTOMER NUMBER: 00136

Mail Stop Provisional Patent Application
Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Sir:

Transmitted herewith for filing is a PROVISIONAL APPLICATION of

Vitali Pavlovich ZUBOV, Moscow, Russia
Lutz PLOBNER, Erkrath, Germany
Dimitri Valerjewich KAPOUSTINE, Moscow, Russia
Hamlet BALAYAN, Yerevan, Republic of Armenia
Makhmud Rakhmotovich MUVDINOV, Pervaya, Russia
Gottfried BREM, Hilgertshausen, Germany

for SORBENT MATERIAL HAVING A COVALENTLY ATTACHED PERFLUORINATED
SURFACE WITH FUNCTIONAL GROUPS. The application comprises a 24-
page specification.

Accompanying this application for filing is:

X Filing Fee: Small Entity, \$80.00 X Large Entity, \$160.00

Check No. 63952, in the amount of \$160.00, is enclosed to cover the
Filing Fee. The Commissioner is hereby authorized to charge
payment of any fees set forth in §§1.16 or 1.17 during the pendency
of this application, or credit any overpayment, to Deposit Account
No. 06-1358. A duplicate copy of this sheet is enclosed.

CORRESPONDENCE ADDRESS:

JACOBSON HOLMAN PLLC
400 Seventh Street, N.W.
Washington, D.C. 20004

Respectfully submitted,

JACOBSON HOLMAN PLLC

By William E. Player 22769
for Reg. No. 31,409

WEP:mch

Sorbent material having a covalently attached perfluorinated surface with functional groups

5

10 The present invention relates to a sorbent material having a solid support substantially modified with a fluorinated polymer coating which is covalently attached to the support and the fluorinated polymer coating is containing at least one functional group, methods of obtaining the sorbent material, the use of these materials for separation of substances, a chromatographic column or
15 cartridge at least partially filled with the sorbent material of the invention, a membrane-like device comprising the sorbent material of the invention, a device comprising the sorbent material of the invention in loose form as well as a miniaturized device comprising the sorbent material.

20 The development of composite sorbent materials for stationary phases has led to substances with a wide range of chromatographic properties. These materials with modified surfaces are widely used in separation processes. Mostly, a hydrophilic support material, such as silica gel, is modified with hydrophobic moieties like alkyl chains of different length.

25 Many efforts have been made to improve the properties of the chromatographic material in terms of chemical stability, the field of applications or selectivity. Modification of the surface material moderates the properties of the stationary

phases and influences the separation which is based on hydrophilic, hydrophobic or ion-ion interactions.

Fluorinated moieties, taking advantage of the higher polarity of the C-F bond over the C-H bond, give rise to a broadened spectrum of application opportunities. It is known that perfluorinated polymers have, apart from their exceptional chemical stability, a unique range of sorption properties which allows to use them in separation processes of complex real or test mixtures of biopolymers, especially of nucleic acid or proteins, but the poor mechanical stability of these materials does not allow a direct use of perfluorinated polymers in chromatographic separation processes.

Efforts have been made to get composite fluorinated materials, in particular sorbents manufactured on the basis of solid porous silica gels. This is to combine in the same material the mechanical strength, determined by the porous nature of the inorganic matrix and the specific sorption properties of the fluorinated polymeric modifying compound.

EP 1 148 945 discloses such a material having a solid support of controlled pore glass and a coating of crosslinkable olefinic oligomers. Fluorination of the oligomer coated support is effected with gaseous xenon difluoride (XeF_2), optionally under inert gas conditions, or with a mixture of fluorine and an inert carrier gas. The composite material thus obtained is suitable for chromatographic separations. It is also used in the isolation of DNA out of complex mixtures, where apart of DNA also RNA, proteins, low molecular substances and salts are present. But, because of the exclusively hydrophobic nature of these materials, there are certain difficulties in using them with aqueous solutions of biopolymers and they are much more used for chromatographic separations in columns with increased pressure (HPLC) and operations using hydrophobic interaction chromatography (HIC).

Beside these applications, there is a growing need for applications which lead to the desired products in a fast and economic way, e.g. isolation and purification

- 3 -

of DNA with effective removal of by-products and impurities. The fluorinated surface of the materials of EP 1 148 945 is, due to their essentially hydrophobic characteristics, not able to provide the capacity for the isolation of biopolymers without denaturing conditions, because of the lack of capability in wetting the
5 fluorinated surface..

Another drawback of the composite materials according to EP 1 148 945 is, that fluorination with xenon difluoride or fluorine gas will not lead to a uniform surface of the coating and a perfectly fluorinated layer of the coating is hardly achieved.

- 10 The polymeric coating of the composites of EP 1 148 945 is manufactured via sorption of crosslinkable oligomers on particles of the porous support. The missing chemical attachment of the coating does not correspond to the need of permanent availability of chemically stable stationary phases with exactly the same quality and the increasing demands of validated analysis protocols.
15 Furthermore, the not desirable release of hydrogen fluoride during the production process is unavoidable.

Therefore, the object of the present invention is to provide a sorbent material with an advanced surface for biotechnological applications, such as isolation and separation of biopolymers, primarily in aqueous media, with improved access
20 area of the separation surface in a separation medium and improved stability of the coating for the construction of material suitable for chromatographical applications like HPLC and fast sample preparations via solid phase extraction in compact cartridges for PCR-applications.

According to the invention, a sorbent material is provided having a solid support
25 with a fluorinated polymer coating wherein the support is substantially modified with the fluorinated polymer coating which is covalently attached to this support and the fluorinated polymer coating is containing at least one functional group.

The functional groups exhibiting hydrophilic properties provide an essentially better wetting of the inner and outer surfaces of the pores of the sorbent material.

5 Preferably the support of the sorbent material of the invention is porous inorganic material selected from the group comprising inorganic metal oxides, such as oxides of aluminium, zirconium, silicon and/or iron. In particular preferred is porous glass which is used in the way of controlled pore glass (CPG). Typically, this shows pores in the range of 10 to 200 nm (medium pore size).

10 In another aspect of the invention, the support is an organic material, preferably of porous structure such as crosslinked polystyrenes, polyacrylates, and polyethylenes.

Preferably, the support containing inorganic or organic materials is in particle-like or monolithic membrane-like form.

15 To create a uniform surface equally equipped with fluorine moieties, the support is modified with a perfluorinated or at least partially fluorinated polymer. This uniformity of the coating effectively increases the selectivity of binding of biomacromolecules.

20 To enhance the chemical stability and durability of the sorbent material, the polymer coating is covalently attached to the support via Si-O-C, C-C, C-O-C and other chemical bonds, according to the chemical nature of the support material.

The polymer coating preferably has a thickness of about 10 to 250 Angström.

The functional groups modifying the hydrophobic properties in contrast to a solely fluorinated surface are selected from the group consisting of hydroxy, amino, carboxyl, linear amides, cyclic amides, bromide, and aldehyde.

The low chemical reactivity of fluorinated compounds hampers the manufacturing of composite materials according to the invention. These difficulties are circumvented by placing the support material in a reaction vessel with connection to a vacuum pump. At lower temperature and/or lower pressure compared to ambient conditions fluorine containing olefinic monomer(s), preferably tetrafluoroethylene and hexafluoropropylene, are deposited in the reaction vessel. The support material is irradiated using high energy radiation to create reactive surface radicals. The following reaction is influenced by subsequent introduction of at least one second monomer having at least one olefinic moiety and at least one additional function group. With controlled addition of monomers bearing at least one hydrophilic functional group to the gas phase of the reaction vessel at a predetermined stage of the irradiation the heterogenic phase co-polymerisation is performed and the hydrophilic functional groups of choice are introduced.

This leads to an increase of hydrophilicity at the perfluorinated surfaces with maintenance of specific sorption properties and the capability of hydrophobic, hydrophilic and ion-ion interactions for the separation of biopolymers is provided. The surface radicals of the support will be obtained by the way of X-ray, gamma, UV or ozone treatment.

Another advantage of the introduction of reactive functional groups is the opportunity of further chemical modification of the surface and with that the optimisation of selectivity of the materials of the invention.

In another embodiment of the invention, a mixture of olefinic fluorine containing monomer(s), preferably tetrafluoroethylene and/or hexafluoropropylene, and at least one second monomer containing at least one olefinic moiety and at least

one additional functional group are placed in a solution of a keton, preferably acetone, or an alcohol, preferably 2-propanol in a closed reaction vessel. The solution is irradiated with high energy radiation to initiate the reaction of the solvent, the fluorine containing monomer(s) and other monomer(s) containing at least one functional group.

After co-telomerisation the deposition of the reaction product of keton and/or alcohol and the mixture of fluorine containing monomer(s) and other monomer(s) containing at least one olefinic moiety and at least one additional functional group is effected with a subsequent temperature increase, thermally or via microwave-irradiation.

The second monomer(s) containing at least one functional group are preferably selected from the group consisting of vinyl acetate, allyl alcohol, allyl bromide, (meth)acrylic acid, vinylacetic acid, N-vinyl pyrrolidone, (di)alkylamine, acrolein, and hydroxyethyl(meth)acrylate.

The sorbent material according to the invention is useful in separation processes, enhancing the ease of handling and the speed of these processes. Preferably, the substances to be separated are nucleic acids and/or proteins. A conventionally used chromatographic column or cartridge can be filled, at least partially, with the sorbent material of the invention. The sorbent material of the invention behaves similar to other solid chromatographic supports so that the methods for filling chromatographic columns or cartridges can be used in an analogous manner. The support for carrying out chromatographic separations can also be provided in the form of a membrane-like item comprising the sorbent material of the invention, wherein the sorbent material is embedded in a polymeric matrix such as a nylon membrane. Also other membrane materials which are used in preparation, isolation or separation of biomolecules can be used as matrix for embedding a sorbent material of the present invention.

In order to ease the use of a chromatographic material of the invention it is advantageous to provide the sorbent material according to the invention in a

loose form or a chromatographic column or cartridge or membrane-like device together with filter materials, reagents and/or buffers or other devices or chemicals for performing sample preparation and chromatographic separations. This item can especially be provided in form of a kit or a miniaturized device in
5 form of chips or microreactors. The chromatographic separation is not limited in its scale. It can be used in any chromatographic operation for separation, isolation, identification, purification and/or detection of biomolecules, in particular nucleic acids, in preparative or analytical scale.

The present invention provides a product with advanced sorption properties that
10 allows to use this product for chromatography of biomacromolecules according to the object of the invention. The perfluorinated support material shows a uniform coating, which is attached by covalent bonds at the surface of the support material.

The invention is further explained in the following examples which are
15 understood to be not limiting.

Example 1

10 g of GPB-Trisopor-500 (effective pore diameter 50 nm) are placed into the glass ampoule and connected with the vacuum plant. The ampoule is vacuumized to a pressure of about 13 - 14 mBar during the heating using of the
20 sand bath to 573 K. After that 1 g of tetrafluoroethylene was frozen into the ampoule. The ampoule was sweated out from the plant and it was heated to room temperature and incubated at room temperature for 2 h. After that the ampoule was cooled to 77 K with the rate about 0.1 K/sec and it was irradiated with using a γ -source with dose about 5 Mrad. After that the ampoule was
25 heated to the room temperature, incubated for 3 h and it was connected to the vacuum plant for further vacuumization to the pressure of about 10^{-3} mBar. After that the acroleine vapors (0.1 g, $P = 270$ mBar) were added into the system (the monomer expenditure was observed by the pressure decreasing).

The plenty of the monomer was frozen into the reserve vessel. After that the ampoule was disconnected from the plant.

Example 2

5 The synthesis of the sorbent was carried out as in Example 1, but the freezing process was with the velocity of irradiation of about 0.3 K/sec and dose of about 6 Mrad.

Example 3

The synthesis of the sorbent was carried out as in Example 1, but the 2-hydroxyethylmetacrylat was used as a monomer (0.2 g, P = 333 mBar).

10 Example 4

The synthesis of the sorbent was carried out as in Example 1, but diallylamine was used as a monomer (0.05 g, P = 200 mBar).

Example 5

15 The synthesis of the sorbent was carried out as in Example 1, but allylbromide was used as a monomer (0.2 g, P = 333 mBar).

Example 6

The solution of the mixture containing the monomers was prepared as follows: 900 ml of the dry acetone placed into the glass or iron vessel was frozen and was vacuumized repeatedly to remove the air. After that the mixture containing 20 the tetrafluoroethylene (5.3 % from the weight of acetone) and vapors of another monomer (0.33 % from the weight of acetone) were added into the same vessel (to the pressure about 1.6 Bar) and were frozen. After that the vessel was closed hermetically and the temperature was increased to 20°C. The

vessel containing the monomers with acetone was irradiated by γ -source (Co^{60}) for 2 h with the dose about 5 Hr/h. After the irradiation the reactor was opened and unreacted monomer was removed. IR-spectroscopy data were obtained which were shown the presence of the acetone fragments in the content of the
5 cotelomere.

Example 7

The solution of the cotelomers was prepared as in Example 6, but hexafluoropropylene was used as a monomer.

Example 8

10 The solution of the cotelomers was prepared as in Example 6, but allylbromide was used as a monomer.

Example 9

The solution of the cotelomers was prepared as in Example 6, but the N-vinylcaprolactame was used as a monomer.

Example 10

The solution of the cotelomers was prepared as in Example 6, but the N-vinylpyrrolidone was used as a monomer.

Example 11

20 The solution of the cotelomers was prepared as in Example 6, but 2-hydroxyethylmethacrylat was used as a monomer.

Example 12

The solution of the cotelomers was prepared as in Example 6, but 2-propanol was used as a telogene and hexafluoropropylene was used as a monomer.

Example 13

- 5 The solution of the cotelomers were prepared as in Examples 7 and 12. After the preparing the solution were mixed with the proportion 9:1.

Example 14

- 10 3 g support material, e.g. GPB Trisopor-500 (effective pore diameter 50 nm and effective surface 112 m²/g) are placed in a glass ampoule connected with the vacuum pump. The ampoule with the support is evacuated to a pressure of 10 mBar within 30 min. After that the valve to the pump is closed and another valve, connected to a reservoir is opened, this containing 40 ml of the telomer liquid tetrafluoroethylene in acetone in a concentration of 0.36 % (w/v). The solution is piped to the ground of the reaction vessel, the reactor is filled and the
15 solution is added to the pores of the support. Then the reactor is brought to atmospheric pressure.

- In the following the vessel is treated 15 min with supersonic for uniform distribution of the telomer solution within the pores of the support. Then the vessel is connected with a rotary evaporator and the solvent (acetone) is
20 evacuated via water jet pump (16 mm Hg) and a steam bath. Evacuation of acetone in the vacuum rotary evaporator is continued for 3 h via oil pump. Finally, the sorbent is brought into a drying cabinet and dried for 3 h at 200°C.

The thus obtained sorbent material is powdery, hardly wettable with water, white and odourless.

Example 15

Coating of the support surface is carried out as in Example 14, but 6 g support GPB Trisopor-500 and 40 ml 0,12 % (w/v) tetrafluoroethylene in acetone is used. After obtaining the dried powdery sorbent the vessel is evacuated and a new 40 ml telomer portion is added. This procedure is repeated once again and all stages of the drying process are performed as in Example 14.

Example 16

The synthesis of the sorbent is carried out as in Example 15, but the support is treated only twice with 40 ml 0,18 % (w/v) telomer solution.

10 Example 17

The synthesis of the sorbent is carried out as in Example 14, but MPS-1150 GCh is used as support material (effective pore diameter 100 nm, effective surface 33 m²) and treated with 40 ml telomer solution tetrafluoroethylene 0,106 % (w/v).

15 Example 18

The sorbent is obtained as described in Example 15 with the support material of Example 17. Treatment with 40 ml telomer solution 0,053 % (w/v) takes place twice.

Example 19

20 The sorbent is obtained as described in Example 18 with threefold treatment with 40 ml telomer solution 0,032 % (w/v).

Example 20

The sorbent was prepared as in Example 19, but the carrier was treated by the cotelomer solution as obtained in Example 7.

Example 21

- 5 The sorbent was prepared as in Example 19, but the carrier was treated by the cotelomer solution as obtained in Example 8.

Example 22

The sorbent was prepared as in Example 19, but the carrier was treated by the cotelomer solution as obtained in Example 9.

10 **Example 23**

The sorbent was prepared as in Example 19, but the carrier was treated by the cotelomer solution as obtained in Example 10.

Example 24

- 15 The sorbent was prepared as in Example 19, but the carrier was treated by the cotelomer solution as obtained in Example 11.

Example 25

The sorbent was prepared as in Example 19, but the carrier was treated by the cotelomer solution as obtained in Example 12.

Example 26

The sorbent was prepared as in Example 19, but the carrier was treated by the cotelomer solution as obtained in Example 13.

Example 275 **Testing of the Sorbents****A. Mercury Porometry**

The porogrammes obtained by testing the sorbents based on the macroporous glasses GPB-Trisopor 500 and MPS 1150 GCh show the distribution of the pores in differential and integral manner and allow to determine the medium pore size
10 of the sorbent as well as the effective thickness of the polymeric layer, which is 5 - 7,5 nm.

B. Determination of Hydrolytic Stability

Samples of the sorbent based on macroporous glasses GPB-Trisopor 500 and MPS 1150 GCh and the samples of unmodified supports were incubated under
15 basic conditions (Tris-buffer, pH 10,5) for 32 h. Aliquots of the supernatant were taken at predetermined times of incubation and mixed with a 0,5 M solution of ammonium molybdat and sulphuric acid (1/200 of volume of aliquot). The adsorption of silicon molybdate indicates the release of silicates from the surface of the support and the interaction with ammonium molybdate. The smallest
20 peak was found by incubation of the sorbents obtained according to Examples 14 and 19. The hydrolytic stability of the modified sorbents was increased to the 2,8- to 23-fold.

Example 28

The sorbents were prepared as in Example 19. The sorbent samples (0.1 g of each ones) were incubated in 5 ml in a mixture of equal volumes of methanol and 0.01 M Tris aqueous solution (pH 11.0) under slow mixing at room temperature for 16 h. The aliquots (1 ml) of the supernatant from each sample were collected every hour. The equal volumes of the 0.05 M sodium molybdate aqueous solution in the presence of sulfuric acid were added to each supernatant. After that the aliquots (1 ml) of 0.1 M sulfosalicylic acid aqueous solution were added to each sample and the samples were tested by UV-spectroscopy. The data obtained show that the sorbents were characterized by the higher hydrolytic stability in comparison with the unmodified carrier, especially during the first hours of the process. That confirmed the obtaining of the stable composite sorbents with the solid unbroken polymer layer immobilized on the surface of the carrier.

Example 29

The sorbents were prepared as in Example 19. The tests for hydrolytic stability were carried out as in the Example 14, but the sorbent samples were incubated in 5 ml of 0.01 M Tris. The results obtained show that prepared sorbents are also characterized by the high hydrolytic stability.

Example 30

The sample of obtained sorbents (as in Examples 14 - 26) were incubated in acetone at room temperature at slow mixing for 16 h. The aliquots were collected from each sample every hour. The aliquots were tested by UV-spectroscopy. The data obtained confirm the only insignificant increasing of the monomer content in the tested solutions even after 6 h of the incubation. That confirmed the presence of covalently bonded polymer phase on the surface of the carrier.

Example 31

The cotelomer solutions were prepared as in Examples 8, 9 and 11. The aliquots (100 ml) were collected from the tested solutions and the thin films were formed on the surface of the NaBr glass after removing the solution. The obtained immobilized films were studied by IR-spectroscopy. After that the studied films were thermosetted at 200°C for 3 h. The thermosetted films were also studied by IR-spectroscopy. The obtained data show that the bands at 2960-2950, about 1400, 1300 and about 1200 cm^{-1} were constantly observed for all of the tested films. Those bands are corresponding to the IR-spectrum of the pure tetrafluoroethylene. At that the band about 1700 cm^{-1} was significantly decreased after the thermosetting that indicates the removing of telogen moieties during the heating of the film. This process is accompanied with the chemical bond formation between the carrier surface and the polymer phase. The residual band at 1700 cm^{-1} was observed for the sample solution was obtained as in Example 11. It can be explained as a result of a chemical binding of 2-hydroxyethylmethacrylate monomer during the copolymerization process. For the samples of 8 and 9 the additional bands at 2330 cm^{-1} (with using of N-vinylcaprolactame as a comonomer) as well as about 3000 and 1600 cm^{-1} (with using of allylbromide as a comonomer) were observed as a result of a chemical binding of the corresponding comonomers.

Protocol for tissue lysis and extraction of genomic DNA from tissue samples (e.g. Typifix)

5

The kit contains all necessary reagents for lysis of cells or tissue and genomic DNA purification. The resulting DNA is suitable for most enzymatic reactions (restriction digests, PCR, sequencing etc.).

10

Compared to most other protocols not DNA is retained by the column resin, but proteins, detergents and low molecular weight compounds are. DNA flows through the column during a short, one-step purification procedure.

15

Storage conditions:

Store all kit components at +4°C.

20

Materials:

Buffer G1

50 mM Tris-HCl pH 8,0; 10 mM mM Na₂-
EDTA, 20 mg/ml Proteinase K,

Buffer G2

1 % sodium dodecylsulfate

25

Materials not provided:

Eppendorf tubes (1.5 ml)

30

- 17 -

Preparation of buffers

1. immediately before use add 1,6 ml of deionized water to a tube with lyophilised buffer G1
- 5 2. dissolve the constituents by vortexing the tube
3. shortly centrifuge the tubes containing buffer G2 to collect the components at the bottom of the tubes
4. transfer the solution of buffer G1 completely to one aliquot (tube) of buffer G2
- 10 5. mix the buffers to get a homogeneous solution
6. the mixture contains all components necessary for tissue or cell lysis and is now ready for use (The mixture should be used immediately. Therefore, prepare only as much buffer as needed for the number of samples to be analysed.)

15

Cell or tissue lysis

- 20 1. transfer cells or a tissue probe into an Eppendorf tube (max. 20 mg fresh weight)
2. add 300 µl of lysis buffer mixture (see preparation of buffers) to each cell or tissue sample (< 20 mg fresh weight).
3. incubate the samples at 60°C overnight with constant shaking at ~800 rpm in an Eppendorf-Thermomixer (Typifix samples are dry. If fresh tissue is
- 25 used, shorter incubation periods may be sufficient for complete lysis.)
4. clear the lysate by centrifugation for 3 min. at 20.000 x g
5. Take 120 µl from the clear supernatant for DNA purification. The remaining lysate can be stored at -20°C.

30

Purification of DNA

- 18 -

6. open the spin-columns, remove the caps (Parafilm) at the outlet and place the columns in Eppendorf tubes
7. transfer 120 µl of the cleared supernatant from step 4. onto the columns and close the lid (the lysate enters the upper resin layer)
- 5 8. incubate the columns for 3 min. at room temperature
9. spin the tube with the column at 400 x g for 1 min.
10. The flow-through contains the purified DNA. Discard the column and use the DNA immediately or store it at -20°C.

10

Protocol for lysis and isolation of genomic DNA from Bacteria

The kit contains all necessary reagents for lysis of bacterial cells and DNA purification. It is approved for many Gram(-) as well as Gram(+) bacteria. The
15 resulting DNA is suitable for most enzymatic reactions (restriction digests, PCR, sequencing etc.).

Compared to most other protocols not DNA is retained by the column resin, but proteins, detergents and low molecular weight compounds are. DNA flows
20 through the column during a short, one-step purification procedure.

20

Materials provided:

Buffer B1	2 mg/ml Lysozym; 100 mM Tris-HCl pH8,9;
25 Buffer B2	1% sodium dodecylsulfat 1,5 mM Na ₂ -EDTA
Buffer B3	20 mg/ml Proteinase K
RNase	1 mg/ml RNase A

30 Preparation of buffers

1. immediately before use add 1100 μ l of deionized water to a vial with lyophilised buffer B1 and dissolve the constituents by vortexing the tube (the resuspended buffer should be used immediately or stored frozen at -20°C)
- 5 2. shortly centrifuge the tubes containing buffer B2 to collect the components at the bottom of the tubes, then add 550 μ l deionized water to 1 vial with buffer B2 and vortex (the prepared buffer is stable for 14 d at room temperature)
- 10 3. add 550 μ l deionized water to 1 vial with buffer B3 and dissolve the constituents (the resuspended buffer should be used immediately or stored at $+4^{\circ}\text{C}$)

Lysis of bacterial cells:

- 15 1. grow an overnight culture of bacteria in a suitable medium (e.g. LB, CSB)
2. transfer 0,5 ml of the culture to 1,5 ml Eppendorf tubes
3. pellet the cells by centrifugation at $6000 \times g$ for 1 min, remove and discard the supernatant
- 20 4. add 100 μ l buffer B1 and 20 μ l RNase solution to the bacterial cell pellet
5. gently vortex the tube to resuspend the cells
6. incubate the tube for 10 min at 60°C constantly shaking (1200 rpm, Eppendorf thermomixer)
- 25 7. add 50 μ l of buffer B2 and continue the incubation as in step 6 for 5 min. at 60°C
8. then add 50 μ l of buffer B3 and continue the incubation at 60°C for 25 min. (as described in step 6) in the thermomixer
9. In most cases the lysate should be clear after the incubation. If it is not, centrifuge the tube for 3 min. at $20000 \times g$ to pellet cell debris.
- 30

Purification of DNA

10. open the spin-columns, remove the caps (Parafilm) at the outlet and place the columns in Eppendorf tubes
- 5 11. transfer 120 μ l of the clear lysate from step 9. onto the columns and close the lid (the lysate enters the upper resin layer)
12. incubate the columns for 3 min. at room temperature
13. centrifuge the tube with the column at 400 x g for 1 min.
14. The flow-through contains the purified DNA. Discard the column and use
10 the DNA immediately or store it at -20°C .

Claims

1. Sorbent material having a solid support modified with a fluorinated polymer coating characterized in that the support is substantially modified with the fluorinated polymer coating which is covalently attached to the support and the fluorinated polymer coating is containing at least one functional group.
2. The sorbent material according to claim 1 wherein the support is a porous inorganic material selected from the group comprising inorganic metal oxides, such as oxides of aluminium, titanium, zirconium, silicon oxides, and/or iron oxides.
3. The sorbent material according to claim 1 wherein the support is an organic material, preferably of porous structure such as cross-linked polystyrenes, polyacrylates, and polyethylenes.
4. The sorbent material according to claims 2 and 3 wherein the support is in particle-like or monolithic membrane-like form.
5. The sorbent material according to claim 1 wherein the support is modified with a perfluorinated or at least partially fluorinated polymer.
6. The sorbent material according to claim 1 wherein the polymer coating is covalently attached to the support via Si-O-C, C-C, C-O-C and other chemical bonds, according to the chemical nature of the support material.
7. Sorbent material according to claim 1, wherein the surface functional groups are selected from the group consisting of hydroxy, amino, carboxyl, linear amides, cyclic amides, bromide, and aldehyde.
8. Sorbent material according to claim 1, wherein the polymer coating has a thickness of preferably 10 to 250 Å.

9. Method of obtaining a sorbent material according to claims 1 - 8, characterized in depositing at lower temperature and/or pressure compared to ambient conditions fluorine containing monomer(s) on the support having surface radicals, and subsequent introduction of at least one second monomer having at least one olefinic moiety and at least one additional functional group.
10. Method of obtaining a sorbent material according to claims 1 - 8, characterized in deposition of a reaction product of ketone and/or alcohol and a mixture of fluorine containing monomer(s) and at least one second monomer containing at least one olefinic moiety and at least one additional functional group with a subsequent temperature increase.
11. Method according to claim 9 - 10, wherein the second monomer(s) are preferably vinylacetate, allyl alcohol, allylbromide, (meth)acrylic acid, vinylacetic acid, N-vinylpyrrolidone, (di)alkylamine, acrolein, and hydroxyethyl(meth)acrylate.
12. Method according to claim 9, wherein the surface radicals of the support will be obtained by high energy radiation such as X-ray, gamma, UV or by ozone treatment.
13. Method for separation of substances using the sorbent material according to claims 1 - 8 in a separation process.
14. Method for separation of substances according to claim 13, wherein the substances are nucleic acids and/or proteins.
15. A chromatographic column or cartridge filled at least partially with the sorbent material according to claims 1 - 8.

16. A membrane-like device comprising the sorbent material according to claims 1 - 8, which is embedded in a polymeric matrix, such as a nylon membrane.
- 5 17. A device comprising the sorbent material of claims 1 - 8 in loose form preferably for batch or magnetic separation.
18. A miniaturized device comprising the sorbent material of claims 1 - 8 for detection and/or separation of bioorganic compounds.
- 10 19. Miniaturized device according to claim 18 in form of chips or microreactors.

Abstract

The present invention relates to a sorbent material having a solid support substantially modified with a fluorinated polymer coating which is covalently
5 attached to the support and the fluorinated polymer coating is containing at least one functional group, methods of obtaining the sorbent material, the use of these materials for separation of substances, a chromatographic column or cartridge at least partially filled with the sorbent material of the invention, a membrane-like device comprising the sorbent material of the invention, a device
10 comprising the sorbent material of the invention in loose form as well as a miniaturized device comprising the sorbent material.

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/EP03/012517

International filing date: 10 November 2003 (10.11.2003)

Document type: Certified copy of priority document

Document details: Country/Office: US
Number: 60/475,785
Filing date: 05 June 2003 (05.06.2003)

Date of receipt at the International Bureau: 05 March 2004 (05.03.2004)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.